

SurTec® 102

Ultra Sonic Cleaner with Corrosion Protection

Properties

- liquid
- temporary corrosion protection after drying
- suitable for iron, steel, aluminium and zinc plated steel
- quickly demulsifying

Application

SurTec 102 is used for cleaning and passivating in single- or multi-chamber ultrasonic installations.

concentration: 1-4 %vol SurTec 102

temperature: 40-80 °C

application time: 1-10 min

Technical Specification

(at 20 °C)	Appearance	Density (g/ml)	pH-value (at 10 g/l)
SurTec 102	liquid, yellowish	1.040 (1.03-1.05)	9.7 (9-10.5)

Maintenance and Analysis

Analyse and adjust the concentration of SurTec 102 regularly.

Sample Preparation

Take a sample at a homogeneously mixed position. Let it cool down to room temperature. If the sample is turbid, let the turbidity settle down and decant or filter the solution.

SurTec 102

reagents: 0.1 N hydrochloric or sulfuric acid
indicator: methyl orange

procedure:

1. Pipette 20 ml bath sample into a 250 ml Erlenmeyer flask.
2. Dilute to approx. 100 ml with deionised water.
3. Add 3 drops of indicator.
4. Titrate with 0.1 N acid from yellow to red.

calculation: consumption in ml · 0.219 = %vol SurTec 102

Ingredients

- anionic surfactants
- nonionic surfactants
- amines
- salts of organic acids

Stock Keeping

In order to prevent delays in the production process, per 1,000 l bath the following amounts should be kept in stock:

SurTec 102 Ultra Sonic Cleaner 30 kg

Product Safety and Ecology

The safety instructions and the instructions for environmental protection have to be followed in order to avoid hazards for people and environment. The Material Safety Data Sheets (according to European legislation) contain explicit details for this.

The following hazard designations and classifications into water hazard classes (WHC) have to be taken into account:

<u>product</u>	<u>hazard designation</u>	<u>water hazard class</u>
SurTec 102	Xi - Irritant	WHC 2

Warranty

We are responsible for our products in the context of the valid legal regulations. The warranty exclusively accesses for the delivered state of a product. Warranties and claims for damages after the subsequent treatment of our products do not exist. For details please consider our [general terms and conditions](#).

Further Information and Contact

In our forum, you can discuss topics of the surface technology:

<http://forum.SurTec.com/>

If you have any questions concerning the process, please contact your local technical department: <http://SurTec.com/International.html>